

## IN THE CLAIMS

Please cancel claims 3, 4, 12 to 17, 22 and 23 without prejudice, and amend the claims as follows:

1. (Currently Amended) A vertical drawing method for producing a cylindrical glass body, said method comprising:

continuously feeding a glass cylinder to a heating zone having a vertically oriented heating tube;

zonewise softening the glass cylinder;

drawing a glass strand from the softened glass cylinder; and

cutting the glass strand to size to obtain the cylindrical glass body; and

an adjusting operation that comprises sensing a value for a first radial xy-position of a longitudinal cylinder axis of the glass cylinder or of a test glass cylinder in a first horizontal sensing plane, drawing the glass cylinder or the test glass cylinder arranged in the first xy-position into a test glass strand, and carrying out the following steps once or repeatedly:

- a) measuring an actual state of a radial circular or annular dimension of the test glass strand,
- b) determining a deviation between the actual state and a desired state of the circular or annular dimension relative to a magnitude and position of said deviation relative to an inner wall of the heating tube during drawing,
- c) calculating a corrected xy-position of the longitudinal cylinder axis on the basis of a correction factor and the magnitude and position of the deviation,

- d) repositioning the glass cylinder or the test glass cylinder in the heating tube such that the longitudinal cylinder axis extends at least in the first horizontal sensing plane in the corrected xy-position, and
  - e) drawing the glass cylinder or the test glass cylinder in the corrected xy-position to obtain a further test glass strand; **and**  
**wherein the test glass strand is tubular, and wherein the measurement of the actual state of radial circular or annular dimension of the test glass strand comprises measuring the wall thickness extension of the tubular test glass strand.**
- 2. (Previously Presented) The method according to claim 1, wherein the sensing of the value for the first radial xy-position comprises producing an optical image of the glass cylinder in the first sensing plane and at least part of the heating tube or a calibration body in stationary relation with the heating tube, and evaluating the optical image.
  - 3. (Canceled)
  - 4. (Canceled)
  - 5. (Currently Amended) The method according to claim **1** **3**, wherein the tubular test glass strand is drawn with an outer diameter of not more than 50 mm.
  - 6. (Previously Presented) The method according to claim 1, wherein the measurement of

the actual state of radial circular or annular dimension of the test glass strand is carried out during drawing, wherein the circular or annular dimension is determined at a plurality of measurement points distributed over a circumference of the test glass strand.

7. (Currently Amended) The method according to claim 1, 3 wherein the measurement of the actual state of radial circular or annular dimension of the test glass strand is carried out on pieces of the test glass strand that have been cut to length, using a stationary wall thickness measuring device.
8. (Currently Amended) The method according to claim 1, 3, wherein in a tubular test glass strand, the xy-position and the corrected xy-position are separated by a distance A, as defined by the following dimensioning rule:

$$A = K \times \text{wall lopsidedness}$$

where K is a correction factor ranging between 5 and 40 if the wall lopsidedness is determined as a differential amount between a maximum value and a minimum value of the wall thickness.

9. (Previously Presented) The method according to claim 1, wherein a value is determined for the first radial xy-position of the longitudinal cylinder axis of the glass cylinder in a second horizontal sensing plane.

10. (Previously Presented) The method according to claim 1, wherein installing the glass cylinder in the heating tube comprises computer-controlled transportation of the glass cylinder to the corrected xy-position.
11. (Previously Presented) The method according to claim 1, wherein the glass cylinder is of test material.
12. (Canceled)
13. (Canceled)
14. (Canceled)
15. (Canceled)
16. (Canceled)
17. (Canceled)
18. (Previously Presented) The method according to claim 1, wherein the cylindrical glass body is quartz glass.

19. (Currently Amended) The method according to claim 13, wherein the tubular test glass strand is drawn with an outer diameter between 10 mm and 20 mm.
20. (Currently Amended) A method for drawing a glass body from a glass cylinder, said method comprising:
- positioning the glass cylinder in a vertically oriented heating tube;
  - feeding said glass cylinder continuously to a heating zone in the heating tube and softening the glass cylinder therein;
  - drawing a glass strand from the softened glass cylinder; and
  - cutting the glass strand to size to obtain the cylindrical glass body;
  - said positioning of the glass cylinder comprising
  - drawing a test strand from the cylinder or from a test cylinder supported with a longitudinal axis thereof extending vertically through an xy-position in a generally horizontal sensing plane,
  - measuring a geometrical attribute of the test strand;
  - deriving a deviation of the geometrical **attribute property** from a desired value of said geometrical attribute **of the said geometrical attribute**,
  - deriving a corrected xy-position from said deviation, and
  - positioning the cylinder or the test cylinder so that the longitudinal axis thereof extends through the corrected xy-position,
- wherein the geometrical attribute includes a data value indicative of lopsidedness**

**and a data value indicative of the orientation of lopsidedness relative to the heating tube,**  
**and**

**wherein the test strand is tubular, and the data value indicative of lopsidedness is**  
**derived from a plurality of measurements of wall thicknesses of the tubular strand.**

21. (Previously Presented) The method of claim 20, wherein the steps of drawing, measuring, deriving, and positioning are repeated to yield a second corrected xy-position to which the cylinder is moved.

22. (Canceled)

23. (Canceled)

24. (Currently Amended) The method of claim **20 22**, wherein the xy-position is sensed by producing and evaluating an optical image of the glass cylinder in the horizontal sensing plane, and said positioning of the cylinder is accomplished automatically by a processor responsive to the sensed **xy-position** ~~**XY position**~~ and the geometrical property.